



1K Filler YK 700

TECHNICAL DATA SHEET

1K-FILLER-YK 700

Application and product information

- Y.K Filler is pigmented nitrocellulose Filler blended with modified alkyd resins and selected fillers. It is formulated to give a high covering property, good sanding ability and good elasticity.

Technical properties

Test	Method	Result
Appearance	Visual	White – Grey
Solids by Weight	n Oven @150 C for 30 min.	58 ± 2%
Specific Gravity (gm/ml)	Specific gravity Cup	1.25 ± 0.1
Viscosity (Centipoise)	Brookfield @Sp 5, RPM 20	45.000 ± 5000 CP
Drying time	Surface dry	20 min
Drying time	Complete dry	45 : 65 min.

- Y.K filler can be used for all type of wooden furniture, chairs, turned pieces, clothes– hooks, picture molding and related products.
- Clean well the surface to be treated with Make sure it is dry and free from silicone, wax and grease. Sand the surface well with manual sanding or automatic sanding machine then clean the surface.

The information this data sheet is given to the best of our knowledge based on laboratory testing and Practical experience. However, as the product is often used under conditions beyond our control we can't guarantee anything but the quality of the product itself

1K-FILLER-YK 700

- By spraying (4 -3 atm) / brushing For all woods; 1 – 2 coats thinned at %30 Thinner. Sand the surface well with manual sanding or automatic sanding machine. Ensure that the surface is clean and well prepared prior to final coating.
- All tools should be cleaned with Wash nitro Thinner

- Minimum 1 year if The product stored in dry space provided with adequate Ventilation at 25 c & ° %65 R.H

IMPORTANT

Always follow the product instructions and use appropriate personal protective equipment during preparation and application.