



YK NC Glossy Varnish 700

TECHNICAL DATA SHEET

Application and product information

- Y.K Gloss is a superior quality transparent Gloss varnish for wooden surfaces based on nitrocellulose and special additives for wooden surfaces

Technical properties

Test	Method	Result
Appearance	Visual	Gloss / Transparent
Solids by Weight	In Oven @150 C for 30 min	36 ± 2%
Specific Gravity (gm/ml)	Specific gravity Cup	0.97 ± 0.02
Viscosity (Sec.)	Brookfield @Sp.2, RPM 10	7500 CP
Gloss	Gloss meter	87 ± 5
Drying time	Surface dry	15 - 20 min
Drying time	Complete dry	60 – 70 min.

- Excellent resistance to scratching and abrasion. Excellent Transparency. Fast drying.

The information this data sheet is given to the best of our knowledge based on laboratory testing

and Practical experience. However, as the product is often used under conditions beyond our control

we can't guarantee anything but the quality of the product itself.

- interior wooden surfaces. wooden and parquet floors, furniture...etc.
- The surface must be clean and free from oil, grease, dirt, lime scale and any other foreign contaminants. The sandpaper is applied in the direction of the wood fruit, and it is taken into account to wipe the dust. Close the pores by repeated application of a sealer of Y.K products.

- Dilute the varnish with %100-200 of Thinner. Applying by spray gun (1.3 – 1.4 mm) (3 – 4 bar) with 3-2 coats and flash off time between each coat is 5 minutes.
- All tools should be cleaned with Wash Thinner.
- 24 months in the original package, tightly closed at a temperature of 25 C and %65 R.H and away from direct sunlight and heat.

The information this data sheet is given to the best of our knowledge based on laboratory testing

and Practical experience. However, as the product is often used under conditions beyond our control

we can't guarantee anything but the quality of the product itself.

IMPORTANT

Always follow the product instructions and use appropriate personal protective equipment during preparation and application.